

**SYNTHETIC OIL**

**SAE 5W-30  
API SN/CF; ACEA A3/B3; A3/B4-C3;  
VW504.00/507.00; BMW LL-04**

---

Typical Test Data		
TEST	TEST METHOD	RESULTS
Density at 20°C, g/cm <sup>3</sup>	ASTM D4052	0,841
Kinematic viscosity, 100°C, mm <sup>2</sup> /s	ASTM D445	11
Kinematic viscosity, 40°C, mm <sup>2</sup> /s	ASTM D445	61
Viscosity Index	ASTM D2270	175
Pour point, °C	ASTM D97	-35
Flash point, °C	ASTM D92	232
Total Base Number, mg KOH/g	ASTM D2896	8
Sulphated Ash, % m/m	ASTM D874	1,2

The information given in the typical data does not constitute a specification but is an indication based on current production and can be affected by allowable production tolerances.